

Confidential Report

Our Ref: 23/61677B/01/24







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24

Your Ref: ---

Page: 1 of 7

Client: Gabriel A/S

Hjulmagerve 55 DK-900 Aalborg Denmark

Job Title: Fire Test on One Fabric Sample

Clients Order Ref: --

Date of Receipt: 03 January 2024

Date Test Started: 08 January 2024

Description of Sample: One sample of fabric, which was referenced by the client as;

Tailor, col. 61305

Work Requested: We were asked to test the received sample to the following standard:

BS EN 1021:Parts 1 & 2:2014 – Ignitability of Upholstered Furniture

- subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited



Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24

Your Ref: ---

Page: 2 of 7

Client: Gabriel A/S

FIRE TEST ACCORDING TO BS EN 1021-1:2014

Assessment of the ignitability of upholstered furniture. Part I. Ignition Source 0: Smouldering cigarette

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The materials for testing to Source 0 and 1 were conditioned for a minimum of 24 hours and tested in the environments specified in Clause 7 of BS EN 1021-1 & 2:2014.

The sample was tested in a room of volume 25m³ and 18ºC.

Procedure

The test was carried out in accordance with BS EN 1021-1:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22kg/m³.

Tests were made using ignition source 0.

Requirements

The specimens shall not:-

Smouldering Criteria

- a) display escalating combustion requiring active extinction.
- b) smoulder or burn until it is essentially consumed within the test duration.
- c) smoulder or burn to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) on final examination, show evidence of progressive smouldering.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24 Your Ref: ---

Page: 3 of 7

Client: Gabriel A/S

Requirements (continued)

Flaming Criteria

a) show evidence of flaming initiated by a smouldering source.

Results

Smouldering criteria	Specimen No.		
	1	2	3 ¹
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Smoulders to extremities/full thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of progressive	No	No	
smouldering			

Flaming criteria	1	2	31
Occurrence of flames	No	No	
Specimen Result	NI	NI	
Ignition (I) / Non Ignition (NI)	IVI	IVI	

Any "Yes" in smouldering or flaming criteria means Ignition

Cigarette Test Result Pass

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comments

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-1.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24

Your Ref:

Page: 4 of 7

Client: Gabriel A/S

FIRE TESTS ACCORDING TO BS EN 1021-2:2014

Assessment of the ignitability of upholstered furniture. Part 2. Ignition Source 1: Match flame equivalent.

Pre-Treatment

The material received no pre-treatment as the fabric is stated not to be FR treated.

Conditioning

The sample was conditioned for at least 24 hours at a temperature of $23\pm2^{\circ}$ C and relative humidity of $50\pm5\%$.

The sample was tested in a room of volume 25m³ and 18°C.

Procedure

The test was carried out in accordance with BS EN 1021-2:2014. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The sample was tested over non-fire retardant polyurethane foam with a density of approximately 20-22kg/m³.

Tests were made using ignition source 1.





1066



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24

Your Ref: ---

Page: 5 of 7

Client: Gabriel A/S

Requirements

The specimens shall not:-

Smouldering Criteria

- a) display escalating combustion requiring active extinction.
- b) smoulders until it is essentially consumed within the test duration.
- c) smoulder to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) smoulder for more than one hour.
- e) show evidence of charring, other than discolouration, for more than 100mm in any direction apart from the nearest part of the original position of the source.

Flaming Criteria

- a) display escalating combustion requiring active extinction.
- b) burns until it is essentially consumed within the test duration.
- c) burns to the extremities of the specimen, or through the full thickness, within the duration of the test.
- d) exhibit any flaming for more than 120 seconds after removal of the burner tube.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

08 January 2024 Date:

Our Ref: 23/61677B/01/24 Your Ref:

> Page: 6 of 7

Client: Gabriel A/S

Results

		Specimen No.	
Smouldering criteria	1	2	3 ¹
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Smoulders to extremities/full thickness	No	No	
Smoulders more than 1 hour	No	No	
In final examination, presence of	No	No	
progressive smouldering			

Flaming criteria	1	2	3 ¹
Unsafe escalating combustion	No	No	
Testing assembly consumed	No	No	
Flames to extremities/full thickness	No	No	
Flames longer than 120 seconds	No	No	
Specimen Result Ignition (I) / Non Ignition (NI)	NI	NI	

Any "Yes" in smouldering or flaming criteria means Ignition

Match Test Result Pass

Note

The test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Comment

An NI designation indicates that the sample meets the performance requirements of BS EN 1021-2.





1066



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 08 January 2024

Our Ref: 23/61677B/01/24

Your Ref: ---

Page: 7 of 7

Client: Gabriel A/S

Where required to make a judgement to any pass/fail criteria an estimation of uncertainty of measurement has been taken into account. Under our Policy we have used a non-binary decision rule.

See our decision rules Policy (https://www.bttg.co.uk/about-us/decision-rules-policy/) for further information.

Uncertainty Budget

The overall uncertainty budget for both BS EN 1021: Part 1 and 2:2014 is as follows:-

Timings: ±2 seconds.

Measurements: ±2mm.

Reported by:...... R Greasley, Laboratory Technician

Enquiries concerning this report should be addressed to Customer Services.





1066