SGS GOVMARK

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 1

| Received:09/1 | 6/2019 Completed: 09/18/2019 | Letter: X5 | RV | P.O.#: | Test Report #: | | 3-34532-5- |
|----------------------------|---|----------------|-------|----------------------|--------------------------------------|-------------|-------------|
| Client's Identification | Style: Morph. Content: 85% Ne End Use: Upholstery. | w Zealand Wool | / 15% | Polyamide. Weight: 4 | 50 g/lm. Color: 11101 | Light Orang | ge. Product |
| | Bente Ellingsoe, Quality Dep Gabriel A/S | artment | | Key Test: | ASTM D 4034/ACT | | 175 |
| | Hjulmagervej 55 DK-9000 Aalborg, Denmark | | | | 011-45-9630-3100 011-45-9811-6125 | Ext: | |

Test Category: Seam Slippage Specifier: ACT LE 2018; V 01/19 PC: 8H dl/SM

NTR 6/16

TEST PERFORMED: ASTM D 4034 - Standard Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics - Plain, Tufted, or Flocked --

As cited by the ACT Voluntary Performance Guidelines (August 2018)

PRODUCT CATEGORY: Upholstery

ACCEPTANCE CRITERIA: 25 lbf minimum average for warp and weft

SEAM CONSTRUCTION:

Seam Allowance: 0.5"

Seam Type: 301 Lockstitch
Thread Type: 100% Nylon Bonded Monocord;

Needle Thread size 8/Bobbin Thread Size 5

Needle:

Size 22 Ball Point

Stitches/Inch: 7 ± 0.5

Specimen results reported to the nearest 0.5 lb force (lbf)

Average reported to the nearest 0.5 lb force (lbf)

| | Specimen # | (lbf) |
|----------------------------|------------|---------|
| | | |
| Warp Yarn Slippage: | 1 | 50.5 SS |
| (seamed in warp direction) | 2 | 52.5 SS |
| | 3 | 46.5 SS |
| | 4 | 50.0 SS |
| | 5 | 47.5 SS |
| | | |
| | Avg | : 49.5 |
| Weft Yarn Slippage: | 6 | 54.5 SS |
| (seamed in weft direction) | 7 | 62.0 SS |
| | 8 | 73.0 SS |
| | 9 | 61.0 SS |
| | 10 | 54.0 SS |
| | | |
| | Avg | : 61.0 |

ABBREVIATIONS WHICH MAY BE USED:

SS = Seam Slippage

SB = Seam break before 1/4" slippage

FB = Fabric break before 1/4" slippage

FBS = Fabric break at Seam before 1/4" slippage

(Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 email: govmark.accounting@sgs.com

Page 2

| | 6/2019 Completed: 09/18/2019 | Letter: X5 | RV | P.O.#: | | Test Report #: | | 3-34532-5- |
|----------------------------|--|----------------------------|-----------|-------------------|----------|----------------------------|-----------|---------------|
| Client's Identification | Style: Morph. Content: 85% Ne End Use: Upholstery. | w Zealand Wo | ool / 15% | Polyamide. Weight | : 450 g/ | lm. Color: 11101 | Light Ora | ange. Product |
| | Bente Ellingsoe, Quality Dep Babriel A/S | artment | | Key Tes | t: AST | M D 4034/ACT | | 175 |
| | Ijulmagervej 55 DK-9000 Aalborg, Denmark | | | | | 5-9630-3100 5-9811-6125 | Ext: | |
| | | | | | | × | | |
| REMARKS: N | Ione. | | | | | | | |
| | | | | | | | | |
| CONCLUSION: | Based on the above Res | ults and Ac | cceptar | ce Criteria, th | ne iter | n tested: | | |
| | | | | | | | | |
| [x] Comp | olies; [] Does not compl | У | | | | | | |
| CERTIFICATI | ON: I certify that the cocedures and equipment s | above resul | | re obtained afte | er test | ing specimens | s in ac | cordance |
| CERTIFICATI | ON: I certify that the | above resul | | | er test | cing specimens | s in ac | cordance |
| CERTIFICATI with the pr | CON: I certify that the cocedures and equipment s | above resul pecified ab | oove. | tit | er test | ing specimens | s in ac | cordance |
| CERTIFICATI with the pr | CON: I certify that the cocedures and equipment s | above resul pecified ab | lis Pet | tit | er test | ing specimens | s in ac | cordance |