

# Test Report

Report No.: A 972505-1



DANISH  
TECHNOLOGICAL  
INSTITUTE


Gregersensvej  
DK-2630 Taastrup  
Tel. +45 72 20 20 00  
Fax +45 72 20 20 19

info@teknologisk.dk  
www.teknologisk.dk

**Assignor:** Gabriel A/S  
Hjulgagervej 55  
9000 Aalborg

Page 1 of 1  
Chf/leln  
Order no.: 972505  
No. of appendices: 1

**Subject:** Upholstery fabric designated: Omega 68093 Green. (as per info from the assigner).



**Sampling:** The test material was sampled by the client and received at the Danish Technological Institute 11.03.2021

**Method:** See Appendix 1.

**Period:** The testing was completed 15.03.2021

**Result:** Individual results appear from Appendix 1.

**Storage:** The test material will be destroyed after 6 months, unless otherwise agreed.

**Terms:** The accredited test was carried out according to DANAK's general conditions see [www.danak.dk](http://www.danak.dk) and according to the General Terms and Conditions regarding Commissioned Work Accepted by the Danish Technological Institute, which apply at the time of signing the agreement. The test is only valid for the tested specimen. The test report may only be extracted, if the laboratory has approved the extract.

**Date/place:** 15.03.2021, Danish Technological Institute, Wood and Biomaterials, Textile, Taastrup

**Signature:** Test responsible

Co-signatory



Report no.: A 972505-1  
 Appendix: 1  
 Page: 1 of 1  
 Initials: Chf/leln

<b>Test Methods</b>	<b>Results</b>										
<b>Colour fastness to rubbing:</b> ISO 105-X12:2016 1-5 scale, 5 best rating Rubbing finger: Cylinder 16 mm Force: 9 N Test conditions: 21°C, 65%RH		<table> <thead> <tr> <th></th> <th><u>Warp direction</u></th> <th><u>Weft direction</u></th> </tr> </thead> <tbody> <tr> <td>Staining:</td> <td>4-5</td> <td>4-5</td> </tr> <tr> <td>Change in colour</td> <td>5</td> <td>5</td> </tr> </tbody> </table>		<u>Warp direction</u>	<u>Weft direction</u>	Staining:	4-5	4-5	Change in colour	5	5
	<u>Warp direction</u>	<u>Weft direction</u>									
Staining:	4-5	4-5									
Change in colour	5	5									