



Date of Issue: 4/24/2024 Report Number: 23-003121

Revision Number:1

Date Order Received: 10/05/2023

For the Account of: Gabriel A/S

Hjulmagervej 55

9000 Aalborg Denmark

		Ü		
Client's Identifica	ation: An	naze Loop col.63147		
dark yellow orange				
		CERTIF	FICATE OF TESTING	
TEST PERFORM a) Abrasion Res TEST RESULTS		sistance of Textile Fabrio	cs (Oscillatory Cylinder Metho	od) ASTM D4157-13(2017); CFFA-1 (
Number of Double Rubs			Warp (Length) Specimens	Fill (Width) Specimens
Specimen #1 Specimen #2			Slight wear Slight wear	Slight wear Slight wear
INTERPRETATION USED Solution 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears. □ Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.				
NOTES Abradant Used: Samples Backed Masking Tape Tension: Compression:	with		k □ Wire Screen	
General Contract Upholstery No apprecial			e or wear after 15,000 double rul e or wear after 30,000 double rul	
Based on the above Results and the A.C.T. St ☐ Unrated ☐ General Contract Upholstery ☐ Heavy Duty Upholstery		Standard, the item tested:		
	certify that the above		ter testing specimen in accordan	ce with the procedures and equipment
Berta Stii	/er			
Authorized Signature			_	Date Order Completed: 04/24/2024

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1