



Date of Issue: 6/7/2023  
 Report Number: 23-001469  
 Revision Number: 2  
 Date Order Received: 04/28/2023

For the Account of: Gabriel A/S  
 Hjulmagervej 55  
 9000 Aalborg Denmark

Client's Identification: SoftNext col 1201  
 BLIND DYE WASHING

### CERTIFICATE OF TESTING

**TEST PERFORMED:** Pilling Resistance and Other Related Surface Changes of Textile Fabrics : Brush Pilling Tester ASTM D3511/D3511M-16

#### TEST RESULTS

	Rating
Left	4.5
Center	4.5
Right	4.5
Average Rating	4.5

#### RATING SYSTEM

- Class 5.0 No Pilling
- Class 4.0 Slight Pilling
- Class 3.0 Moderate Pilling
- Class 2.0 Severe Pilling
- Class 1.0 Very Severe Pilling

#### NOTES

- Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity
- Sampling Method:** As Received
- Viewing Apparatus:** Macbeth Lightbooth
- Viewing Option:** 45 degree
- Rating Standard:** ADJD3512 Photographic Standards
- Running Times:** 4 minutes brushing / 2 minutes pilling

#### ACCEPTANCE CRITERIA

- A.C.T. Standard:** Acceptance Criteria
- Upholstery Class 3 minimum

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 05/04/2023