



Softlines

Test Report	No. 28514447	Date: 12 <sup>th</sup> March 2024	Page 1 of 2
-------------	--------------	-----------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description		:	Medley Col 60999
Customer		:	Gabriel; Hjulmagervej 55, DK, 9000 Aalborg
Submitted by		:	Louise Agersnap Scherer
Style Number		:	Medley Col 60999
Colour		:	Not Given
Product type		:	Upholstery
Fiber content		:	None Given
Test Performed	*	:	Selected test(s) as requested by applicant
Sample Receiving Date Testing Period Test Result(s)		:	1 <sup>st</sup> March 2024 1 <sup>st</sup> March 2024 – 12 <sup>th</sup> March 2024 For further details, please refer to the following page(s).

## **Conclusion:**

Test Property	Results
Abrasion Resistance	-
Pilling Resistance	-

\* Sent to UK accredited UKAS Testing Centre

\*\* Sent to in group Turkey accredited Testing Centre

Signed for and on behalf of TÜV Rheinland UK LTD

## Christopher Clarke Digitally signed by Christopher Clarke Date: 2024.03.12 12:05:41 Z



Chris Clarke Laboratory Supervisor

Test result is drawn according to the kind and extent of tests performed.

Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.





Softlines

Test Report	No. 28514447	Date: 12 <sup>th</sup> March 2024	Page 2 of 2
-------------	--------------	-----------------------------------	-------------

Results:

		Result	
	Specimen 1	Specimen 2	Specimen 3
End point reached, three thread breakdown	105,000	105,000	105,00
Overall		105,000	
Colour Change At 3000 (rubs)	4-5	4-5	4-5

## Pilling Resistance

(BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric)

No cleansing		
Sample	Average Result	
After 2000 Rubs Rating	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5	
After 5000 Rubs Rating	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5	

-End of Test Report-