

<b>Test Report</b>	No. 28513849	Date: 11 <sup>th</sup> July 2023	Page 1 of 2
--------------------	--------------	----------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:


<b>Sample Description</b>	:	Select col.60131
<b>Customer</b>	:	<b>Gabriel; Hjulmagervej 55, DK, 9000 Aalborg</b>
<b>Submitted by</b>	:	Bente Ellingsoe
<b>Style Number</b>	:	-
<b>Colour</b>	:	60131
<b>Product type</b>	:	Upholstery fabric
<b>Fiber content</b>	:	-

Test Performed : Selected test(s) as requested by applicant  
 Sample Receiving Date : 5<sup>th</sup> July 2023  
 Testing Period : 5<sup>th</sup> July 2023 – 11<sup>th</sup> July 2023  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	Results
Pilling	-

Signed for and on behalf of  
TÜV Rheinland UK LTD

 Digitally signed  
by Dathan Stone  
Date: 2023.07.11  
12:08:28 +01'00'

**Dathan Stone**  
**Laboratory Team Leader**



8400

*Test result is drawn according to the kind and extent of tests performed.  
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*



<b>Test Report</b>	No. 28513849	Date: 11 <sup>th</sup> July 2023	Page 2 of 2
--------------------	--------------	----------------------------------	-------------

**Results:**

<b>Pilling Resistance</b> (BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric) No cleansing required	
Sample	Average Result
After 2000 Rubs Rating	4-5 Fuzzing 4-5 Pilling 5 Matting
After 5000 Rubs Rating	4-5 Fuzzing 4 Pilling 5 Matting

∟

-End of Test Report-