

**West Yorkshire  
Materials  
Testing Service**

Page 1 of 2

PO Box 5, Morley, LS27 0QP  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
Head of Laboratory G. Briggs C. Text ATI

**Client:** Gabriel  
Hjulgagervej 55  
Postbox 59  
DK-9100 Aalborg  
Denmark

**Entry No:** 46239-01 (Amended)

**Date Received:** 7<sup>th</sup> March 2011

**Client's Description:** Sample of Fabric Art. Gaja

**TEST REPORT**

**Test Required:** Fire Test

**FIRE TESTS ACCORDING TO BS 476: PART 7: 1987 (AS AMENDED)  
(Method for classification of the surface spread of flame of products)**

**Date of Test: 24/06/2011**

**Conditioning**

The sample was conditioned to constant mass at a temperature of 23 +/- 2°C and a relative humidity of 50 +/- 10% and maintained in this condition until required for testing.

**Procedure**

The test was carried out in accordance with BS 476: Part 7: 1987. The specimens were tested stuck down onto 12 mm calcium silicate board using PVA adhesive.

The following were recorded:-

- a) the time at which the flame front crosses each vertical reference line;
- b) the maximum extent of flame spread during the first 1.5 min from the start of the test;
- c) the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- d) the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5 min and the final flame spread results were compared with the standard class limits and a classification was assigned.

-----End of Page -----


*This is hereby certified to be a correct return of the tests made of the items referred to herein.*

G Briggs, Head of Laboratory, Date of original 6<sup>th</sup> July 2011  
Date of 1<sup>st</sup> amendment 16<sup>th</sup> November 2011  
Date of 2<sup>nd</sup> amendment 1<sup>st</sup> December 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



\* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



**West Yorkshire  
Materials  
Testing Service**

Page 2 of 2  
PO Box 5, Morley, LS27 0QP  
Nepshaw Lane South, Morley, Leeds  
Tel 0113 253 0241 Fax 0113 252 7029  
Head of Laboratory G. Briggs C. Text ATI

**Client:** Gabriel  
Hjulgagervej 55  
Postbox 59  
DK-9100 Aalborg  
Denmark

**Entry No:** 46239-01 (Amended)

**Requirements**

The class limits for flamespread, detailed in BS 476: Part 7: are set out below

|         | Flame spread at 1.5 min (mm) | Final flame spread (mm) |
|---------|------------------------------|-------------------------|
| Class 1 | 165 (+ 25)                   | 165 (+ 25)              |
| Class 2 | 215 (+ 25)                   | 455 (+ 45)              |
| Class 3 | 265 (+ 25)                   | 710 (+ 75)              |
| Class 4 | Exceeding Class 3 limits     |                         |

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.

**Results**

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

| Time for flame Spread to reach (s) (mm) |     |     |     |     | Flame spread at 1.5 min (mm) | Maximum flame spread (mm) | Time to reach maximum flame spread (s) |
|---|-----|-----|-----|-----|------------------------------|---------------------------|--|
| 165                                     | 215 | 265 | 455 | 710 |                              |                           |  |
|   |     |     |     |     | 70                           | 70                        | 60                                     |
|   |     |     |     |     | 70                           | 70                        | 60                                     |
|   |     |     |     |     | 70                           | 70                        | 60                                     |
|   |     |     |     |     | 70                           | 70                        | 60                                     |
|   |     |     |     |     | 70                           | 70                        | 60                                     |
|   |     |     |     |     | 70                           | 70                        | 60                                     |

The results indicate that the sample met the performance requirements of Class I.

Subcontracted test made by a UKAS Accredited Laboratory.

-----End of Document -----

This is hereby certified to be a correct return of the tests made of the items referred to herein.

G Briggs, Head of Laboratory, Date of original 6<sup>th</sup> July 2011  
Date of 1<sup>st</sup> amendment 16<sup>th</sup> November 2011  
Date of 2<sup>nd</sup> amendment 1<sup>st</sup> December 2011

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.



\* This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.