



Date of Issue: 4/24/2024 Report Number: 23-003121

Revision Number:1

Date Order Received: 10/05/2023

For the Account of: Gabriel A/S

Hjulmagervej 55 9000 Aalborg Denmark

Client's Identification: Amaze Loop col.63147

dark yellow orange

CERTIFICATE OF TESTING

TEST PERFORMED: Pilling Resistance and Other Related Surface Changes of Textile Fabrics: Brush Pilling Tester ASTM D3511/D3511M-16

TEST RESULTS

	Rating
Left	5.0
Center	5.0
Right	5.0
Average Rating	5.0

RATING SYSTEM

Class 5.0 No Pilling
Class 4.0 Slight Pilling
Class 3.0 Moderate Pilling
Class 2.0 Severe Pilling
Class 1.0 Very Severe Pilling

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

Sampling Method: As Received
Viewing Apparatus: Macbeth Lightbooth

Viewing Option: 45 degree

Rating Standard: ADJD3512 Photographic Standards
Running Times: 4 minutes brushing / 2 minutes pilling

ACCEPTANCE CRITERIA

A.C.T. Standard: Acceptance Criteria
Upholstery Class 3 minimum

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

uthorized Signature Date Order Completed: 04/24/2024

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1