

Received: 01/23/2020	Completed: 02/05/2020	Letter: U3	RV	P.O.#:	Test Report #: 3-36905-3-
Client's Identification	Style: Focus Melange vers. 7A. Content: 100% New Zealand Wool. Weight: 380 g/lm. Color: 61214 Beige. Product End Use: Upholstery.				
Tested For: Bente Ellingsoe, Quality Department	Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Key Test: ASTM D 5034/ACT	165
				Tel: 011-45-9630-3100	Ext:
				Fax: 011-45-9811-6125	

Test Category: Tensile Specifier: ACT LE 2019; V 12/19 PC: 8H dl/SM
 NTR 9/15

TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --

As cited by the ACT Voluntary Performance Guidelines (March 2019)

PRODUCT CATEGORY:	ACCEPTANCE CRITERIA (for warp and weft):
-----	-----
<input checked="" type="checkbox"/> Upholstery	50 lbs. minimum average
<input type="checkbox"/> Wrapped Panels & Upholstered Walls	35 lbs. minimum average
<input type="checkbox"/> Draperies	No requirement

RESULTS:

Direction	Specimen #	(lbs)
-----	-----	-----
Warp:	1	110
	2	125
	3	108
	4	118
	5	113
	Avg:	115
Weft:	1	34
	2	30
	3	108
	4	107
	5	109
	6	109
	7	93
	8	31
	Avg:	78

REMARKS: None.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Does not apply to drapery fabrics

Received: 01/23/2020	Completed: 02/05/2020	Letter: U3	RV	P.O.#:	Test Report #:	3-36905-3-
Client's Identification	Style: Focus Melange vers. 7A. Content: 100% New Zealand Wool. Weight: 380 g/lm. Color: 61214 Beige. Product End Use: Upholstery.					
Tested For: Bente Ellingsoe, Quality Department	Gabriel A/S Hjulgagervej 55 DK-9000 Aalborg, Denmark			Key Test: ASTM D 5034/ACT	165	
				Tel: 011-45-9630-3100	Ext:	
				Fax: 011-45-9811-6125		


CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

 AUTHORIZED SIGNATURE

SGS

/mg

/pm



Bobby Brown

(Page 2 of 2)

FEB 19 2020