

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 1

| Received:07/1 | 1/2016 Completed: 08/16/2 | 2016 Letter: H | RG | P.O.#: | Test Report #: | : | 3-14269-0- |
|---|---|------------------|-----------|-----------|--|------|------------|
| Client's Identification | | ition: 100% Wool | . Weight: | 530 g/lm. | | | |
| Tested For: Bente Ellingsoe, Quality Department Gabriel A/S | | | | | Key Test: ASTM D 4966/ACT SP 60K | | |
| | Hjulmagervej 55 DK-9000 Aalborg, Denmark | | | | Tel: 011-45-9630-3100 Fax: 011-45-9811-6125 | Ext: | |

LE: 2012e1 V 03/15

CODE: 200,000 RQ

/jd

TEST PERFORMED: ASTM D 4966 Martindale Abrasion Method Standard Test Method for Abrasion Resistance of Textile Fabrics (Upholstery Fabric Classification)

Abradant:

Plain weave cross-bred worsted wool standard fabric, 5.8 oz/sq yd

Pressure:

 $1.74 \text{ psi } \pm 0.04 \text{ psi } (12 \text{ kPa})$

Foam disk is inserted if test item is less than 14.7 oz/yd2.

APPROXIMATE FABRIC WEIGHT (as measured by Govmark): 11.3 oz/yd²

INTERPRETATIVE OPTIONS:

[x] Option 1: Smooth or Textured Surface Fabrics --

[x] Woven Fabric:

The end point (wear) is reached when two or more threads have broken; loss of special effect yarn or pile exposing base fabric.

[] Knitted Fabric: The end point is reached when a hole appears.

[] Option 2: Slightly Napped, Brushed, Sueded Fabrics -The end point (wear) is reached when there is a change in shade
or appearance that is sufficient to cause a customer to complain.
The shade end point (wear) is reached when a color change is
assigned a Grey Scale rating of 3 or less.

RATING SYSTEM FOR OPTION 1:

- 5 None or negligible change in appearance
- 4 Slight change in appearance
- 3 Moderate change in appearance.
- 2 Objectionable change in appearance (broken yarns, floating yarns, loss of pile, core yarn exposed, a hole, etc.)
- 1 Severe change in appearance (complete fabric break, base fabric exposed, or running and pulling of knit)

RATING SYSTEM FOR OPTION 2: (AATCC Grey scale for Color Change)

Grade 5 - No color change

Grade 4 - Slight color change

Grade 3 - Noticeable color change

Grade 2 - Considerable color change

Grade 1 - Excessive color change

(Page 1 of 3)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 2

| Received:07/ | 11/2016 Complet | ed:08/16/2016 | Letter: H | RG | P.O.#: | | Test Report #: | | 3-14269-0- |
|---|------------------------------------|---------------|---------------|--------|-----------|----------|----------------------------------|-------|------------|
| Client's Identification | Style: Gaja | Composition: | 100% Wool. We | eight: | 530 g/lm. | | | | |
| Tested For: Bente Ellingsoe, Quality Department Gabriel A/S | | | | | Key | Test: AS | STM D 4966/ACT S | P 60K | 300 |
| | Hjulmagervej 55 DK-9000 Aalborg | g, Denmark | | | | | 1-45-9630-3100 1-45-9811-6125 | Ext: | į |

RESULTS: Visual evaluation (see page 1 for Rating System)

| No. of Rubs | Rating |
|-------------|--------------|
| | |
| 5,000 | 4.5 |
| 10,000 | 4.5 |
| 20,000 | 4 |
| 30,000 | 4 |
| 40,000 | 4 |
| 50,000 | 3 |
| 55,000 | 3 |
| 60,000 | 2 |
| | Broken yarns |

NOTE: For tests exceeding 50,000 rubs, the abradant fabric is changed at 50,000 rubs if breakdwon has not been reached.



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 3

| | | | | | | | | • | . 484 2 |
|----------------------------|------------------------------------|----------------------------|--------------|------------|-------------|---------|---|------------|------------|
| Received:07/1 | 1/2016 Complete | d:08/16/2016 J | ∡etter: H | RG P. | O.#: | | Test Report # | : | 3-14269-0- |
| Client's Identification | | Composition: 1 | 00% Wool. We | eight: 530 | g/lm. | • | | | |
| G | lente Ellingsoe labriel A/S | , Quality Depa | rtment | | Кеу Т | est: AS | TM D 4966/ACT | SP 60K | 300 |
| | ljulmagervej 55 K-9000 Aalborg, | Denmark | | | | | 1-45-9630-3100 1-45-9811-6125 | Ext: | |
| End Point E | valuation: | | | | | | | | |
| Specimen # | | Number of F End Point | tubs | | | | | | |
| 1 2 3 | | 60,000 60,000 60,000 | | | | | | | |
| | AVG: | 60,000 | | | | | | | |
| REMARKS: N | one. | | | | | | | | |
| Materials - General | ••• | olstery: No | objectiona | ble cha | nge in appe | arance | January 2005) e at 20,000 ruk e at 40,000 ruk | bs | lstery |
| CONCLUSION: | Based on th | e above Resu | lts and Acc | eptance | Criteria, | the it | em tested is 1 | rated for | : |
| [x] Gene | ral Contract | Upholstery; | [x] Heavy | Duty U | pholstery; | [] [| Inrated | | - |
| CERTIFICATION with the pro | ON: I certi | | | | obtained a | fter t | esting specime | ens in aco | cordance |
| AUTHORIZED S | SIGNATURE | | Ms. Phy | llis Pe | ettit | | | | |
| /pm/mo | | | AUG 2 | 9 2016 | | | | | |
| | | | (Page : | 3 of 3) | | | | | |