

Softlines

<b>Test Report</b>	No. 28514119	Date: 3 <sup>rd</sup> January 2024	Page 1 of 2
--------------------	--------------	------------------------------------	-------------

**AMENDMENT TEST REPORT**

The following sample(s) was/were submitted and identified on behalf of the client as:

<b>Sample Description</b>	:	PET Fabric
<b>Customer</b>	:	<b>Gabriel; Hjulmagervej 55, DK, 9000 Aalborg</b>
<b>Submitted by</b>	:	Alexander Holtermann
<b>Style Number</b>	:	New Contour Melange 60359
<b>Colour</b>	:	-
<b>Product type</b>	:	Upholstery fabric
<b>Fiber content</b>	:	100 PET

Test Performed : Selected test(s) as requested by applicant  
 Sample Receiving Date :  
 Testing Period :  
 Test Result(s) : For further details, please refer to the following page(s).

**Conclusion:**

Test Property	Results
Abrasion	-
Pilling	-
Seam Slippage	-

Amendment to style number at client request

Signed for and on behalf of  
TÜV Rheinland UK LTD

**Christopher Clarke** Digitally signed by Christopher Clarke  
Date: 2024.01.03 13:24:12 Z

**Chris Clarke**  
Laboratory Supervisor



8400

*Test result is drawn according to the kind and extent of tests performed.  
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*

<b>Test Report</b>	<b>No. 28514119</b>	<b>Date: 3<sup>rd</sup> January 2024</b>	<b>Page 2 of 2</b>
--------------------	---------------------	--	--------------------

**Results:**

<b>Seam Slippage</b> (BS EN ISO 13936-2:2004)	
<b>Sample</b>	<b>Result</b>
Warp	1.2 mm
Weft	1.2 mm

<b>Pilling Resistance</b> (BS EN ISO 12945-2:2020; Martindale Abrasion & Pilling Tester; Total Load Applied 415g, tested against wool abradent fabric) No cleansing required	
<b>Sample</b>	<b>Average Result</b>
<b>After 2000 Rubs Rating</b>	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5
<b>After 5000 Rubs Rating</b>	Fuzzing: 4-5 Pilling: 4-5 Matting: 4-5

<b>Abrasion Resistance</b> (BS EN ISO 12947-2:2016/AC:2006 according to BS EN 14465); Martindale Wear & Abrasion Tester; 12 kPa Pressure)			
<b>Result</b>			
	<b>Specimen 1</b>	<b>Specimen 2</b>	<b>Specimen 3</b>
End point reached, three thread breakdown	100,000	100,000	100,000
Overall endpoint	100,000		
Colour Change At 3000 (rubs)	4-5	4-5	4-5
Remarks: Grey Scale Rating is based on the step scale of 1 to 5, where 1 is bad and 5 is good Observation Technique:40 fold magnification			

-End of Test Report-