

Softlines

Test Report	No. 28511287	Date: 15 th February 2021	Page 1 of 3
--------------------	--------------	--------------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:


Sample Description	:	Web
Customer	:	Gabriel
Colour	:	4101
Product type	:	Upholstery fabric
Fiber content	:	-

Test Performed * : Selected test(s) as requested by applicant *
 Sample Receiving Date : 11th January 2021
 Testing Period : 11th January 2021 – 15th February 2021
 Test Result(s) : For further details, please refer to the following page(s).

Conclusion:

Test Property	Remarks
Colour fastness to Washing	-
Colour fastness to Dry Cleaning	-
Seam Slippage	-

Signed for and on behalf of
TÜV Rheinland UK LTD

George

 Mehmet
 2021.02.11
 08:28:27 Z

George Mehmet
Laboratory Technician



8400

*Test result is drawn according to the kind and extent of tests performed.
 Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.*



Test Report	No. 28511287	Date: 15 th February 2021	Page 2 of 3
--------------------	--------------	--------------------------------------	-------------

Results:

Colour Fastness To Washing (BS EN ISO 105-C06: 2010) Washing Condition: A2S, 40°C With ECE(B) + Sodium Perborate, 10 Steel Balls.	
Sample	Result
Colour Change	5
Self-Staining	-
Colour Staining	Result
Acetate	5
Cotton	5
Polyamide	5
Polyester	5
Acrylic	5
Wool	5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

Colour Fastness To Dry cleaning (BS EN ISO 105-D01: 2010)	
Sample	Result
Colour Change	5
Self-Staining	-
Colour Staining	Result
Acetate	5
Cotton	5
Polyamide	5
Polyester	5
Acrylic	5
Wool	5
Remark: Grey Scale rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good	

Seam Slippage (BS EN ISO 13936-2:2004)	
Sample	Result
Warp	1.6mm
Weft	1.2mm

-End of Test Report-



TÜVRheinland[®]
Precisely Right.

Softlines

Gabriel[®]

Test Report	No. 28511287	Date: 15th February 2021	Page 3 of 3
--------------------	---------------------	--	--------------------