

Gabriel

Softlines

Test Report No. 28511314	Date: 26 th February 2021	Page 1 of 2
--------------------------	--------------------------------------	-------------

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description	:	Gaja
Customer	:	Gabriel
Colour	:	60003
Product type	:	Upholstery fabric
Fiber content	:	-

Test Performed

Selected test(s) as requested by applicant

Sample Receiving Date

11th January 2021

Testing Period

: 11th January 2021 – 26th February 2021

Test Result(s)

For further details, please refer to the following page(s).

Conclusion:

Test Property	Remarks	
Pilling	-	
Abrasion Resistance ASTM D 4966	Sub-con within group results to follow on completion	

Signed for and on behalf of TÜV Rheinland UK LTD

George Mehmet

2021.02.26

08:32:00 Z

George Mehmet Laboratory Technician U KAS TESTING

8400

Test result is drawn according to the kind and extent of tests performed.

Without permission of the test centre this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. This test report represents the test parameters as requested by the customer based on submitted samples only.



Gabriel

Softlines

	1 20 M 10 10 10 10 10 10 M 10 M 10 M 10		
Test Report	No. 28511314	Date: 26 th February 2021	Page 2 of 2

Results:

Pilling Resistance

(BS EN ISO 12945-2:2000; Martindale Abrasion & Pilling Tester; To fabric) No cleansing required	tal Load Applied 415g, tested against wool abradent
Sample	Average Result
After 2000 Rubs Rating	5
After 5000 Rubs Rating	4-5 (Fuzzing)

Remarks: Pilling Rating

5 - No change

4 - Slight surface fuzzing and/or partially formed pills

- 3 Moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen
- 2 Distinct fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimen surface
- 1 Dense surface and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface

-End of Test Report-