

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Page 1 Received: 06/19/2018 | Completed: 07/03/2018 | Letter: W4 RV **P.O.**#: Test Report #: 3-26795-4-Client's Style: Chili. Content: 75% Post-Consumer Recycled Polyester FR, 25% Polyester FR (FR Inside the Fiber). Finish: None. Identification Weight: 470 g/lm. Color # 66175. End Use: Upholstery Tested For: Bente Ellingsoe, Quality Department Key Test: ASTM D 5034/ACT Gabriel A/S Hjulmagervej 55 Tel: 011-45-9630-3100 Ext: DK-9000 Aalborg, Denmark Fax: 011-45-9811-6125 Test Category: Tensile Specifier: ACT LE 2015; V 08/15 PC: 8H dl/SM NTR 9/15 TEST PERFORMED: ASTM D 5034 - Standard Test Method for Breaking Force of Textile Fabrics (Grab Test) --As cited by the ACT Voluntary Performance Guidelines (January 2015) PRODUCT CATEGORY: ACCEPTANCE CRITERIA (for warp and weft): ______ -----[x] Upholstery 50 lbs. minimum average [] Wrapped Panels & Upholstered Walls 35 lbs. minimum average [] Draperies No requirement RESULTS: Direction Specimen # (lbs) ____ 1 286 Warp: 2 3 286 4 297 5 272 ____ 289 Avg: Weft: 1 223 2 238 3 246 4 235 5 253 6 228 7 248 8 243 ----Avg: 239 REMARKS: None. CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested: [x] Complies; [] Does not comply; [] Does not apply to drapery fabrics (Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 2

Received:06/1	9/2018 Completed: 07/03/2018	Letter: W4	RV	P.O.#:	Test Report #:	3-26795-4-
Client's Style: Chili. Content: 75% Post-Consumer Recycled Polyester FR, 25% Polyester FR (FR Inside the Fiber). Finish: None. Weight: 470 g/lm. Color # 66175. End Use: Upholstery						
Tested For: Bente Ellingsoe, Quality Department				Key Test:	ASTM D 5034/ACT	140
G	Gabriel A/S					
H	Ijulmagervej 55			Tel:	011-45-9630-3100	Ext:
D	K-9000 Aalborg, Denmark			Fax:	011-45-9811-6125	

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE

SGS GOVMARK

/jb /pm

Phyllis Pettit

JUL 1 1 2018

(Page 2 of 2)