

For the Account of:

Gabriel A/S Hjulmagervej 55 9000 Aalborg Denmark

Client's Identification:

Tailor col.62149

CERTIFICATE OF TESTING

TEST PERFORMED: Abrasion Resistance of Textile Fabrics (Martindale Abrasion Tester Method) ASTM D4966-12E1

TEST RESULTS

 Specimen
 Number of Cycles

 1
 75,000

 2
 80,000

 3
 80,000

INTERPRETATION USED

Option 1	The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole
	appears.
X Option 2	The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

NOTES

Test Conditions:	70 ±4°F, 65 ±5% Relative Humidity	
Sampling Method:	As Received	
Abradant Used:	Worsted Wool	Standard Abradant Fabric
Weight:	12 ± 0.3 kPa	
Foam Backing Used:	🗆 No	🗵 Yes
Approximate Weight		
Of Fabric:	10.9 ounces / s	square yard

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria	
General Contract Upholstery	No appreciable breakage or wear after 20,000 cycles	
Heavy Duty Upholstery	No appreciable breakage or wear after 40,000 cycles	

CONCLUSION Based on the above Results and the A.C.T. Standard, the item tested:

General Contract Upholstery

Heavy Duty Upholstery

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 02/09/2024

Date of Issue: 2/13/2024

CERT #3193.01

Rating

Appreciable wear

Appreciable wear

Appreciable wear

Report Number: 24-000220 Revision Number:1

Date Order Received: 02/02/2024

553 76th Street, Byron Center, MI 49315

P: 616-559-6123 E: testlab@applied-lab.com

Page 1 of 1

This laboratory test is not intended to reflect fabric performance under actual conditions. The certification procedure merely measures the performance of samples as received under the predetermined and specific test conditions prescribed by the standard specified. This certificate applies only to the standards or processing identified and to the random sample(s) tested. The test results are representative of the qualities of the piece or lot only to the standard size is presentative of the piece or lot.