

96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 1

Received: 07/25/2018 Completed: 08/02/2018 Letter: L4 RV **P.O.**#: Test Report #: 3-27495-4-Client's Style: Event Screen. Content: 100% Polyester. Finish: None. Weight: 390 g/lm. Color: 60004 Light Grey. End Use: Identification Upholstery. Key Test: ASTM D 4034/ACT 150 Tested For: Bente Ellingsoe, Quality Department Gabriel A/S Tel: 011-45-9630-3100 Ext: Hjulmagervej 55 Fax: 011-45-9811-6125 DK-9000 Aalborg, Denmark

Specifier: ACT LE 2015; V 08/15 PC: 8H Test Category: Seam Slippage

NTR 6/16

TEST PERFORMED: ASTM D 4034 - Standard Test Method for Resistance to Yarn Slippage at the Sewn Seam in Woven Upholstery Fabrics - Plain, Tufted, or Flocked --

As cited by the ACT Voluntary Performance Guidelines (January 2015)

PRODUCT CATEGORY: Upholstery

ACCEPTANCE CRITERIA: 25 lbf minimum average for warp and weft

SEAM CONSTRUCTION:

Seam Allowance: 0.5"

301 Lockstitch Seam Type:

Thread Type: 100% Nylon Bonded Monocord;

Needle Thread size 8/Bobbin Thread Size 5

Size 22 Ball Point Needle:

Stitches/Inch: 7 ± 0.5

Specimen results reported to the nearest 0.5 lb force (lbf) RESULTS:

Average reported to the nearest 0.5 lb force (lbf)

	Specimen #	(lbf)	
Warp Yarn Slippage:	1	110.0 SB	
(seamed in warp direction)	2	102.0 SB	
	3	103.0 SB	
	4	98.5 SB	
	5	110.0 SB	
	Avg:	104.5	
Weft Yarn Slippage:	6	118.5 SB	
(seamed in weft direction)	7	117.0 SB	
	8	111.5 SB	
	9	117.5 SB	
	10	116.0 SB	
	Avg:	116.0	

ABBREVIATIONS WHICH MAY BE USED:

SS = Seam Slippage

SB = Seam break before 1/4" slippage FB = Fabric break before 1/4" slippage

FBS = Fabric break at Seam before 1/4" slippage

(Page 1 of 2)



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

OGO GOVINAIII		e-maii: testing@govm	Page 2
Received:07/25/2018 Completed:08/02/2018 Letter: L4	RV P.O.#:	Test Report #:	3-27495-4-
Client's Style: Event Screen. Content: 100% Polyester. F Identification Upholstery.	Finish: None. Weight: 390 g	z/lm. Color: 60004 Light G	rey. End Use:
Tested For: Bente Ellingsoe, Quality Department Gabriel A/S Hjulmagervej 55 DK-9000 Aalborg, Denmark	Tel:	: ASTM D 4034/ACT : 011-45-9630-3100 : 011-45-9811-6125	150 Ext:
REMARKS: None.			
CONCLUSION: Based on the above Results and Acc [x] Complies; [] Does not comply	eptance Criteria, th	e item testea:	
CERTIFICATION: I certify that the above result with the procedures and equipment specified about the procedures are procedured as a procedure specified about the procedure	ttit	er testing specimens	in accordance